

CHEMISTRY

Element	%
Ti	2.7-3.5
B	0.8-1.2
Fe	0.30 max
Si	0.30 max
V	0.13 max
Others each	0.05 max
Others total	0.10 max

Sample to be taken from mid coil.



FORM

Aluminium rod of diameter 9.7 ± 0.3 mm

Coil weight 180kg \pm 10%

Colour code blue/white

MICROSTRUCTURE

TiAl₃ 90% < 50 μ m
95% < 100 μ m
99% < 200 μ m

TiB₂ 95% of particles < 2 μ m
99% of particles < 5 μ m
The total length of TiB₂ agglomerates should not exceed 25 μ m/cm²

Oxides The total length of oxides should not exceed 500 μ m/cm²

Others Graphite, silicon, carbides, refractory materials and foreign bodies shall not be permitted

GRAIN REFINING

1. Grain refining according to AA TP-1 test to achieve a grain size of 110 μ m (max) after 2 minutes
2. AMG's Advanced DC casting test

MARKING AND PACKAGING

3 coils per pallet, separated by wooden spacers, water proof wrapped and strapped. Each coil shall be identified by means of label showing:

1. Alloy type
2. Coil weight
3. An identification number
4. Supplier's name

Telephone: +44 (0)1709 833 782

Facsimile: +44 (0)1709 828 367

AMG Aluminum UK Ltd, Fullerton Road, Rotherham,
South Yorkshire, S60 1DL, England



www.amg-al.com | enquiries@amg-al.com

Registered in England No. 345279. V.A.T. No. GB 789 6326 65